UCY ENERGY

UCY business services & trading (Germany) GmbH



www.ucy-energy.com

Tall Oil Pitch Product Datasheet

Typical chemical and physical data

Density at 50℃, kg/m³	995
Flash point, open cup, ℃	200
Viscosity, Pa s	
melt at 75 ℃	0.4
melt at 50 ℃	1.8
Acid Value	35
Saponification Value	100
Ash, %	0.4
Sulphur, %	0.4

Typical chemical analysis

Free rosin acids, % by weight	10
Free fatty acids, % by weight	10
Combined Acids, % by weight	40
Unsaponifiables	30

Delivery

Second-hand drums of about 200 kg net.

EINECS number

2324144

The product has been stored in the year 2008.

www.ucy-energy.com